



airpart
THE GLOBAL PARTS PROFESSIONALS

Pbs De-Ice Boot System PROCEDURES

SET UP: To begin the Pbs de-ice boot system application process, you must first have all the proper items available for the job. As you can see in the photo to the right, you will need; a pair of latex gloves, a bucket of water, scrubbing sponge, rinsing sponge, micro fibre applicator, **Pbs Boot Sealant & Pbs Prep**. With products and accessories in hand, you are now ready for prepping and sealing your de-ice boots



STEP 1, CLEANING BOOTS: Put on latex gloves. Apply the **Pbs Prep** directly to the scrubbing sponge as shown in photo. Using the soft side of the sponge, apply the **Pbs Prep** to the de-ice boot. By keeping the de-ice boots wet with **Pbs Prep** for 2-3 minutes all old boot treatments will begin dissolving. At this point use the scrubbing side of sponge to help remove old boot treatments. De-Ice boot should now be ready for rinsing.



STEP 2, RINSING BOOTS: Rinse sponge in clean water as shown in picture to the right. Thoroughly remove all dissolved boot treatments. During this process, you will notice excessive amounts of black oxidation coming from the surface of the boot, this is normal. After drying the de-ice boot, it should be flat black in colour and free of old treatments. Note: If the de-ice boot is not free of all old treatments, you will need to repeat step one. When completely free of old treatments, move to step 3.



STEP 3, APPLYING PBS BOOT SEALANT: Apply **Pbs Boot Sealant** directly on a clean micro fibre applicator. Using the treated micro fibre applicator, apply the **Pbs Boot Sealant** to de-ice boot in one direction. Apply 3-5 coats allowing each coat to dry before applying the next quote. When the de-ice boot is completed, it will have a wet glossy appearance, but will be dry to the touch.



Tel: +44 (0)1494 450366 Fax: +44 (0)1494 465567

E-Mail: sales@airpart.co.uk

Web: www.airpart.co.uk